

MC511A

TECHNICAL DATA BULLETIN

GRADE: MC511A

NEMA: G-11

U.L. LISTED: Y

DESCRIPTION: MC511A is a high strength, glass epoxy laminate that is specially formulated to meet power generation producer's exacting standards where higher strength at elevated temperatures are required. MC511A is certifiable to MIL-I-24768/3, Type GEB and is halogen free to meet the European restrictions.

TYPICAL PROPERTIES

| | | UNITS | VALUE | | |
|---|--------------------------|----------|-------------------|--------|-----------------|
| | | | Thickness Tested | | |
| | | | 0.0625" | 0.125" | 0.500" |
| PHYSICAL PROPERTIES | | | | | |
| Specific Gravity (ASTM D792) | | - | | | 1.91 |
| Rockwell Hardness (ASTM D785)0.250" Build-up | | M Scale | 115 | | |
| Moisture Absorption (ASTM D570)Condition A | | % | 0.10 | | |
| Flexural Strength (ASTM D790) | Condition A | psi | 71,500 / 61,000 | | |
| | LW / CW | (Mpa) | (493.0) / (420.6) | | |
| | Condition E-1/150: T-150 | psi | 37,000 / | | |
| | LW / CW | (Mpa) | (255.1) / | | |
| Izod Impact Strength (ASTM D256) | Condition A | ft-lb/in | | | |
| | LW / CW | (J/cm) | | | |
| | Condition E-48/50 | ft-lb/in | | | 18.00 / 14.00 |
| | LW / CW | (J/cm) | | | (9.61) / (7.47) |
| Bonding Strength (ASTM D229) | Condition A | lb | | | 2,200 |
| | | (kg) | | | (997.9) |

TECHNICAL DATA BULLETIN

GRADE: MC511A

NEMA: G-11

U.L. LISTED: Y

TYPICAL PROPERTIES (continued)

| | | UNITS | VALUE | | |
|--|-------------------------|----------------------|------------------|--------|--------|
| | | | Thickness Tested | | |
| | | | 0.0625" | 0.125" | 0.500" |
| THERMAL PROPERTIES | | | | | |
| Temperature Index ¹ (UL Bulletin 746b) | Electrical / Mechanical | °C | 170 / 180 | | |
| Tg by DMA | | °C | | | 180 |
| Flammability Rating (UL Bulletin 94) | Condition A | Class | HB | | |
| ELECTRICAL PROPERTIES | | | | | |
| Dissipation Factor @ 1 MHz (ASTM D150) | Condition A | - | | | |
| | Condition D-24/23 | - | 0.028 | | |
| Relative Permittivity @ 1 MHz (ASTM D150) | Condition A | - | | | |
| | Condition D-24/23 | - | 4.50 | | |
| Breakdown Voltage (ASTM D149) | Condition A | kVolts | 65 | | |
| Electric Strength (ASTM D149) | Condition A | Volts/mil (kV/cm) | 610 (240.2) | | |
| | Condition D-48/50 | Volts/mil (kV/cm) | 650 (255.9) | | |
| Arc Resistance (ASTM D495) | Condition A | sec | | 185 | |

¹ This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, www.norplex-micarta.com, to determine if the information is the most current available.

Specification writers: Contact Norplex-Micarta for specification values before submission.