

## NP517B TECHNICAL DATA BULLETIN

**DESCRIPTION:** NP517B is a pre-preg composed of a high temperature, electrical grade epoxy resin ( $T_g$ = 170°C), combined with a woven glass substrate. This grade of pre-preg is not flame retardant. With a non-brominated resin system, the product offers high mechanical strength at temperatures up to 170°C. Properly cured, it will retain 50% of its room temperature flexural strength at elevated temperatures (150°C, after conditioning at 150°C for one hour), E-1/150, T-150. This electro-mechanical grade is suitable for power generator slot insulation.

## TYPICAL PROPERTIES

GENERAL PHYSICAL PROPERTIES	UNITS	VALUE
Resin Content	%	35 - 45
Resin Flow	%	15 - 30

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, www.norplex-micarta.com, to determine if information is most current.

Specification writers: Contact Norplex-Micarta for speciation values before submission.

Norplex-Micarta Page 1 12/19/2012