

NP631

TECHNICAL DATA BULLETIN

GRADE: NP631

U.L. LISTED: Y

DESCRIPTION: Hot punching grade with excellent electrical properties and low moisture absorption. Major application is for punched parts for switches and other insulation applications requiring high electrical strength in applications where either moisture is present or in areas of high humidity.

TYPICAL PROPERTIES

		UNITS	VALUE		
			Thickness Tested		
			0.0625"	0.125"	0.500"
PHYSICAL PROPERTIES					
Specific Gravity (ASTM D792)		-			1.38
Rockwell Hardness (ASTM D785)	0.250" Build-up	M Scale	115		
Moisture Absorption (ASTM D570)	Condition A	%			
	Condition D ₁ -24/23	%	1.00		
Flexural Strength (ASTM D790)	Condition A	psi	16,000 / 13,200		
	LW / CW	(Mpa)	(110.3) / (91.0)		
Flexural Modulus (ASTM D790)	Condition A	kpsi	1,100 / 900		
	LW / CW	(Gpa)	(7.6) / (6.2)		
Tensile Strength (ASTM D638)	Condition A	psi		15,000 / 12,000	
	LW / CW	(Mpa)		(103.4) / (82.7)	
Izod Impact Strength (ASTM D256)	Condition A	ft-lb/in			0.65 / 0.60
	LW / CW	(J/cm)			(0.35) / (0.32)
Compressive Strength (ASTM D695)	Condition A	psi			32,000
	Flatwise	(Mpa)			(220.6)
Bonding Strength (ASTM D229)	Condition A	lb			1,100
		(kg)			(499.0)
Shear Strength (ASTM D732)	Condition A	psi	11,500		
	Perpendicular	(Mpa)	(79.3)		

TECHNICAL DATA BULLETIN

GRADE: NP631

U.L. LISTED: Y

TYPICAL PROPERTIES (continued)

	UNITS	VALUE		
		Thickness Tested		
		0.0625"	0.125"	0.500"
THERMAL PROPERTIES				
Temperature Index ¹ (UL Bulletin 746b) Electrical / Mechanical	°C	125 / 125		
Coefficient of Thermal Expansion (IPC-TM 650-2.4.24) X-axis / Y-axis	" / °C x10 ⁻⁶	16.0 / 20.0		
Flammability Rating Condition A (UL Bulletin 94)	Class	HB		
ELECTRICAL PROPERTIES				
Dissipation Factor @ 1 MHz (ASTM D150) Condition A	-			
	Condition D-24/23	-	0.035	
Relative Permittivity @ 1 MHz (ASTM D150) Condition A	-			
	Condition D-24/23	-	4.80	
Breakdown Voltage (ASTM D149) Condition A	kVolts	60		
	Condition D-48/50	kVolts	15	
Electric Strength (ASTM D149) Condition A	Volts/mil (kV/cm)	750 (295.3)		
	Condition D-48/50	Volts/mil (kV/cm)	600 (236.2)	
Arc Resistance (ASTM D495) Condition A	sec	124		
Comparative Tracking Index (ASTM D3638)	Volts	200		

¹ This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, www.norplex-micarta.com, to determine if the information is the most current available.

Specification writers: Contact Norplex-Micarta for specification values before submission.