

RM320

TECHNICAL DATA BULLETIN

GRADE: RM320

NEMA GRADE: L

U.L. LISTED: N

DESCRIPTION: Rolled and Molded Rods made from a fine weave (linen) cotton fabric combined with a phenolic resin system. RM320 is used for electrical and mechanical applications, meeting NEMA L requirements.

TYPICAL PROPERTIES

	UNITS	VALUE ¹		
		Diameter Tested		
			0.500"	
PHYSICAL PROPERTIES				
Specific Gravity	-		1.35	
Rockwell Hardness	M Scale		80	
Moisture Absorption Condition D ₁ -24/23	%		0.85	
Flexural Strength Condition A	psi		20,100	
Tensile Strength Condition A	psi		9,400	
Compressive Strength Condition A	psi		29,000	
THERMAL PROPERTIES				
Temperature Index ² Electrical / Mechanical	°C		115 / 125	
Flammability Rtg. (UL 94) Condition A	Class		HB	

¹ All testing performed to ASTM D-349 unless otherwise indicated.

² NEMA LI-6: This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to contact Customer Service, or preferably our web site, www.norplex-micarta.com, to determine if information is the most current.

Specification writers: Contact Norplex-Micarta for specification values before submission.